

Material

80 HNBR 150351

black

cross linking: peroxidic

revision index	revision date	page	1 / 3
4	10/9/2019		
Physical properties	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	1.18 ±0.02	1.19	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	80 ±5	80	Shore
Micro hardness DIN ISO 48 Verfahren M	80 +5/-8	79	IRHD
Rebound resilience DIN 53512	> 20	30	%
Modulus 100 %, DIN 53504, S2, 23 °C	> 8.5	12.5	MPa
Tensile strength DIN 53504, S2, 23 °C	> 17	24.2	MPa
Elongation at break DIN 53504, S2, 23 °C	> 160	220	%
Compression set DIN ISO 815, Slab I, 22 h, 125 °C, 25 %	< 35	22	%
Tear strength DIN 53507, A, 23 °C	> 10	20	KN/m
Tear strength DIN ISO 34-1, Methode B, 23 °C, (Verfahren a) ohne Einschnitt	---	30	KN/m
Low temperature test ASTM D1329, TR10	---	-18	°C
Low Temperature DIN 53765, DSC	---	-25	°C
Temperature range	-30°C to 140°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance
Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

Material

80 HNBR 150351

black

cross linking: peroxidic

revision index

4

revision date

10/9/2019

page 2 / 3

Country Part

Info ROHS and ELV

Remark

EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III) see DoC

Expires

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

80 HNBR 150351

black

cross linking: peroxidic

revision index

4

revision date

10/9/2019

page 3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com