

# Material

## 85 NBR 131610

black

cross linking: sulfur

**revision index**

1

**revision date**

12/6/2018

**page**

1 / 2

### Physical properties

### nominal range

### typical values

#### Density

DIN EN ISO 1183-1

---

1.27

g/cm<sup>3</sup>

#### Hardness

DIN ISO 7619-1

---

84

Shore

#### Rebound resilience

DIN 53512

---

10

%

#### Modulus

100 %, DIN 53504, S2

---

15.7

MPa

#### Tensile strength

DIN 53504, S2

---

18.5

MPa

#### Elongation at break

DIN 53504, S2

---

135

%

### Declarations of conformity

No data found!

### Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

## Material

### 85 NBR 131610

black

cross linking: sulfur

**revision index**

1

**revision date**

12/6/2018

**page** 2 / 2

**No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -

Fax: -

Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)