

Technical data sheet in accordance with ASTM

Material

EPDM EP701801

black

cross linking: peroxidic

revision index

3

revision date

11/19/2019

page

1 / 3

Physical properties

| | nominal range | typical values | |
|---|---------------|----------------|-------------------|
| Density ASTM D1817 | 1.14 ±0.03 | 1.15 | g/cm ³ |
| Hardness ASTM D2240, Shore A | 70 ±5 | 73 | Shore |
| Tensile strength ASTM D412 | --- | 14.9 | MPa |
| Elongation at break ASTM D412 | --- | 265 | % |
| Modulus 100 %, ASTM D 412 | --- | 697 | Psi |
| Compression set ASTM D395, Slab B, 22 h, 150 °C | --- | 14.2 | % |
| Ozone Resistance ASTM D1171, 40 °C, 70 h, 50 pphm, pass | --- | 0 | Rating |
| Low-temperature resistance ASTM D 2137, 3 min, Method A | --- | -55 | |

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

| Country | Part | Remark | Expires |
|-------------------|------|---|---------|
| Info ROHS and ELV | | EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III) | see DoC |

Change after aging in Air: 70h/150°C

| | | Typ. values | | |
|---------------------------------|-------|-------------|-------------|------------|
| | | Base value | After aging | difference |
| Hardness (ASTM D2240, Shore A) | Shore | 73 | 75 | 2 |
| Tensile strength (ASTM D412) | MPa | 14.9 | 13.1 | -12 % |
| Elongation at break (ASTM D412) | % | 265 | 271 | 2 % |
| weight change | % | | -0.2 | |

Freudenberg

Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner
 Telefon: -
 Fax: -
 Email: FIS.Compound.CRC@fst.com

Technical data sheet in accordance with ASTM

Material

EPDM EP701801

black

cross linking: peroxidic

revision index

3

revision date

11/19/2019

page 2 / 3

Change after aging in Water: 70h/100°C

Typ. values

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

| Base value | After aging | difference |
|------------|-------------|------------|
| 73 | 72 | -1 |
| 14.9 | 12.9 | -13 % |
| 265 | 271 | 2 % |
| | 2.5 | |

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner
Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com

Technical data sheet in accordance with ASTM

Material

EPDM EP701801

black

cross linking: peroxidic

revision index

3

revision date

11/19/2019

page

3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner
Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com