

Technical data sheet in accordance with ASTM

# Material

## FKM FP709204

brown

cross linking: bisphenolically

**revision index**

1

**revision date**

9/26/2017

**page**

1 / 2

### Physical properties

|   | nominal range  | typical values |                   |
|---|----------------|----------------|-------------------|
| <b>Density</b><br>ASTM D297                               | 2.14 ±0.03     | 2.14           | g/cm <sup>3</sup> |
| <b>Hardness</b><br>ASTM D2240, Shore A                    | 70 ±5          | 70             | Shore             |
| <b>Tensile strength</b><br>ASTM D412                      | ---            | 13.1           | MPa               |
| <b>Elongation at break</b><br>ASTM D412                   | ---            | 255            | %                 |
| <b>Tear strength</b><br>ASTM D624, B                      | ---            | 33             | KN/m              |
| <b>Compression set</b><br>ASTM D395, Slab B, 24 h, 200 °C | ---            | 17             | %                 |
| <b>Low temperature test</b><br>ASTM D1329, TR10           | ---            | -17            | °C                |
| <b>Temperature range</b>                                  | -20°C to 225°C |                |                   |

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

|                   | Country | Part | Remark  | Expires |
|-------------------|---------|------|---|---------|
| Info ROHS and ELV |         |      | EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III) | see DoC |

### Freudenberg

Freudenberg Industrial Services GmbH  
 Global Material Technology  
 Nadja Güldner  
 Telefon: -  
 Fax: -  
 Email: FIS.Compound.CRC@fst.com

Technical data sheet in accordance with ASTM

## **Material**

### **FKM FP709204**

brown

cross linking: bisphenolically

| <b>revision index</b> | <b>revision date</b> | <b>page</b> |
|-----------------------|----------------------|-------------|
| 1                     | 9/26/2017            | 2 / 2       |

### **No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### **Freudenberg**

Freudenberg Industrial Services GmbH  
Global Material Technology  
Nadja Güldner  
Telefon: -  
Fax: -  
Email: FIS.Compound.CRC@fst.com