

# Material

## HGW HG200

brown

synthetic fabric - modified phenolic resin, PTFE

### revision index

2

### revision date

12/20/2018

page

1 / 2

### Physical properties

#### typical values

#### Density

IEC 1183-A

1.20

g/cm<sup>3</sup>

#### Compressive Strength

ISO 604, until break (perpendicular to layers), 23 °C

340

MPa

#### compression modulus

ISO 178, 23 °C

2432

MPa

#### Temperature range

dynamic: -40°C to 120°C

short term: 130°C

### Declarations of conformity

No data found!

### Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)

## Material

### HGW HG200

brown

synthetic fabric - modified phenolic resin, PTFE

**revision index**

2

**revision date**

12/20/2018

**page**

2 / 2

### No ASTM D2000 properties available

product type: ring

The given values are based on a limited number of tests on test pieces produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -

Fax: -

Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)