

# Material PE 23200

white

**revision index**  
1

**revision date**  
1/5/2021

**page** 1 / 2

## Physical properties

	nominal range	typical values	
<b>Density</b> DIN 53479, 23 °C	0.93 ±0.02	---	g/cm <sup>3</sup>
<b>Hardness</b> ISO 868, Shore D, 23 °C	61 ±3	---	Shore
<b>Tensile strength</b> ASTM D 4745-79	---	40	MPa
<b>Elongation at break</b> ASTM D 4745-79	---	50	%
<b>E-modulus</b> DIN 53457	---	680	MPa
<b>Temperature range</b>	-200°C to 80°C		

## Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
Conflict Mineral Free			see certificate	see DoC
FDA	USA	Seals	FDA §177.1520	see DoC
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

## Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

**Material**  
**PE 23200**

white

**revision index**

1

**revision date**

1/5/2021

**page** 2 / 2**No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

**Freudenberg**

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -

Fax: -

Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)