

Material

PTFE 177544

white

revision index

4

revision date

6/6/2024

page

1 / 2

Physical properties

typical values

Density

DIN EN ISO 1183-1

g/cm³

Hardness

DIN ISO 48-4, Shore D

56

Shore

Ball indentation hardness

DIN EN ISO 2039-1, 23 °C

29

MPa

Tensile strength

DIN EN ISO 527-1

38

MPa

Elongation at break

DIN EN ISO 527-1/-2

370

%

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
(EG) 10/2011	EU	Seals	(EG) 10/2011	see DoC
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)	see DoC
3-A Sanitary Multi Use Plastics 20-27	USA	Seals	3A-Sanitary	see DoC
FDA	USA	Seals	§ 177.1550	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

PTFE 177544

white

revision index

4

revision date

6/6/2024

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com