

## Material PTFE 19YF

brown

revision index 1	revision date 6/28/2021		page	1/2
Physical properties		nominal range	typical values	
<b>Density</b> DIN EN ISO 1183-1, 23 °C	5		2.64	g/cm³
Hardness DIN ISO 7619-1, Shore D	, 23 ℃		70	Shore
Tensile strength DIN EN ISO 527-1, 23 °C			20	MPa
Elongation at break DIN EN ISO 527-1, 23 °C			180	%

Declarations of conformity No data found!

## Freudenberg

Freudenberg FST GmbH Technology&Innovation Material Compliance Telefon: -Fax: -Email: MaterialCompliance@fst.com



Material PTFE 19YF

brown

revision index

revision date 6/28/2021

page 2/2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

## Freudenberg

Freudenberg FST GmbH Technology&Innovation Material Compliance Telefon: -Fax: -Email: MaterialCompliance@fst.com