

# Material

## PTFE F56110

black

PTFE-carbon compound (10%)

**revision index**  
3

**revision date**  
5/17/2016

**page** 1 / 2

### Physical properties

	nominal range	typical values	
<b>Density</b> DIN 53479 T1, 23 °C	2.15 ±0.03	2.15	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D 2240 Typ D, Shore D, 23 °C, cylinder diameter 50x50 mm, after 3 s	60 ±3	60	Shore
<b>Tensile strength</b> DIN EN ISO 527-1, FD-105, 23 °C, Cross Direction	> 17	19.6	MPa
<b>Elongation at break</b> DIN EN ISO 527-1, FD-105, 23 °C, Cross Direction	> 300	347	%
<b>Temperature range</b>	-150°C to 260°C		

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
ADI Free				see DoC

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: MaterialCompliance@fst.com



## Material PTFE F56110

black

PTFE-carbon compound (10%)

**revision index**

3

**revision date**

5/17/2016

**page** 2 / 2

**No ASTM D2000 properties available**

**This material is characterized by good wear resistance and good thermal conductivity. To a large extent the material is resistant to chemicals**

The given values are based on a limited number of tests on standard test pieces (1,5mm foil) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)

