

# Material

## PTFE F56203

anthracite

**revision index**

2

**revision date**

3/4/2024

**page**

1 / 2

### Physical properties

#### nominal range

#### typical values

#### Density

DIN EN ISO 1183-1, 23 °C

2.05 - 2.11

2.07

g/cm<sup>3</sup>

#### Hardness

DIN ISO 7619-1, Shore D, 23 °C, cylinder diam. 50x50 mm, after 3 s

58 - 63

60

Shore

#### Tensile strength

DIN EN ISO 527-1, FD-105, 23 °C, Cross Direction

> 12

17

MPa

#### Elongation at break

DIN EN ISO 527-1, FD-105, 23 °C, Cross Direction

> 180

225

%

#### Temperature range

-260°C to 200°C

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

#### Country Part

#### Remark

#### Expires

Conflict Mineral Free  
Info ROHS and ELV

see certificate  
EU 2000/53 (ELV) including EU 2011/65 and  
EU2015/863 (ROHS III)

see DoC  
see DoC

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

## Material

### PTFE F56203

anthracite

**revision index**

2

**revision date**

3/4/2024

**page**

2 / 2

#### No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

#### Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)